

the flux at the same time acquiring an amber colour: the metallic button is brittle, and of a tin-white colour.

*Constituent Parts.*

Bismuth,	- - -	27.00
Lead,	- - -	33.00
Silver,	- - -	15.00
Iron,	- - -	4.30
Copper,	- - -	0.90
Sulphur,	- - -	16.30
		—————
		96.50 *

*Klaproth, Beit. b. ii. s. 297.*

*Geognostic and Geographic Situations.*

It has hitherto been found only in the mine named Friedrich-Christian in the Schapbach, in the Black Forest, where it occurs in veins that traverse gneiss, along with copper-pyrites, and quartz, and a smaller quantity of iron-pyrites, and galena or lead-glance.

6. Corneous

---

\* Selb, in his Mineralogical Studies, vol. i. p. 81. states, the quantity of silver in this ore at 20 per cent.