

Third Subspecies.

Malleable Copper-glance or Malleable Vitreous
Copper-ore.

Geschmeider Kupferglanz, *Karsten*.

Id. Leonhard, Tabel. s. 57. *Id. Haus.* s. 72. *Id. Karsten*,
Tabel. s. 62.

External Characters.

Its colour is steel-grey.

Internally it is strongly glimmering.

The fracture is even.

It becomes shining in the streak, and the colour is
changed to lead-grey.

It is malleable.

Specific gravity, 5.099.

Geographic Situation.

It is a rare mineral, having been hitherto found only
in the mines of Catharinenburg in Siberia.

Observations.

Colour, lustre, fracture, and malleability, distinguish
it from the Compact and Foliated subspecies; and its in-
ferior malleability distinguishes it from *Silver-glance* or
Sulphureted Silver-ore.

3. Variegated