

lead-glance, copper-pyrites, iron-pyrites, grey copper-ore, and black silver-ore.

*Geographic Situation.*

It occurs in the Clifton lead-mine, near Tyndrum in Perthshire; in small veins along with galena, in the coal-fields around Edinburgh; at Cumberhead in Lanarkshire, along with galena or lead-glance; at Leadhills it is associated with galena, white lead-ore, sulphate of lead, sparry ironstone, iron-pyrites, brown hematite, azure copper-ore, electric calamine, and wad; the vein-stones are quartz, lamellar heavy-spar, calcareous-spar, brown spar, and mountain-cork. It is met with in all the lead-mines in England and Wales. On the Continent of Europe it forms a constant attendant of galena or lead-glance, whether it occurs in veins or beds; and it maintains the same relation in the lead-mines of Asia, Africa and America.

*Second Kind.*

Fibrous Brown Blende.

Fasrige Braune Blende, *Werner.*

Hepatisches Zinkerz, *Wiedenmann*, Min. s. 906.—Zink sulphure compacte, *Broch.* t. ii. p. 359.—Schaalenblende, *Reuss*, b. iv. s. 342. *Id.* *Karsten*, Tabel. s. 70. *Id.* *Haus.* Handb. b. i. s. 233.—Fibrous Blende, *Aikin*, p. 56.

*External Characters.*

Its colour is reddish-brown.

It