

It is found at Johannegeorgenstadt in Saxony
—at Joachimsthal in Bohemia.

Its matrix is sometimes argillaceous shistus.

DIVISION III.

Bismuth mineralised by sulphur or arsenic; is not quite soluble in acids, and emits a sulphureous smell when ignited.

SPEC. III.

SULPHURISED BISMUTH.

Germ. and Swed. *Wismutglanz.*

Ital. *Bismuto sulfureo.*

Fr. *Mine de bismuth sulphureuse.*

Hung. *Asványos Vismut.*

Cronst. *Wismuthum sulphure mineralisatum.*

Its colour is lead grey and blueish grey—
sometimes variegated.