In the experiment with the crystals of carbonate of zinc from Derbyshire, 14.35 grs. of calx of zinc furnished indeed only 26.8 grs. of arid vitriol of zinc; a deficiency of about $\frac{6}{100}$, occasioned probably by some small inaccuracy of manipulation.

which are sufficiently known to discover it is considered, it appears improbable that the proximate constituent parts of bodies should be united in them, in the very remote relations to each other in which analyses generally indicate them; and, an attention to the subject has led me to the opinion that such is in fact not the case, but that, on the contrary, they are universally, as appears here with respect to arid vitriol of zinc, fractions of the compound of very low denominators. Possibly in few cases exceeding five.

The success which has appeared to attend some attempts to apply this theory, and amongst others, to the compositions of some of the substances above analysed, and especially to the calamine from Bleyberg, induces me to venture to dwell here a little on this subject, and state the composition of this calamine which results from the system, as, besides contributing perhaps to throw some light on the true nature of this ore, it may be the means likewise of presenting the theory under circumstances of agreement with experiment, which, from the surprising degree of nearness, and the trying complexity of the case, may seem to entitle it to some attention.

From this calamine, containing, according to the results of the experiments on the Mendip Hill kind, too small a quantity of carbonic acid to saturate the whole of the calx of zinc in it, and from its containing much too large a portion of water to be in it in the state of mere moisture or dampness, it seems to

C 2